



**PAINTER'S TOUCH®
ULTRACOVER 2X ENAMEL SPRAYS**

DESCRIPTION AND USES

Rust-Oleum® Painter's Touch® Ultra Cover 2X Enamel Sprays are designed to provide long lasting protection and durability. These sprays apply easily, provide excellent coverage and dry fast to a tough attractive finish. Painter's Touch Ultra Cover 2X Enamel Sprays feature an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad to reduce fatigue caused by continuous spraying. Not for use on galvanized metal.

PRODUCTS

Gloss Finish Unless Otherwise Noted

AEROSOL	DESCRIPTION
249859	Semi-Gloss Clear
249094	Sage Green
249117	Clear
249093	Spa Blue
249119	Candy Pink
249120	Brilliant Blue
249123	Berry Pink
249114	Deep Blue
249124	Apple Red
249098	Navy Blue
249116	Colonial Red
249113	Grape
249863	Cranberry
249097	Purple
249095	Red Orange
249089	Winter Gray
249091	Warm Yellow
249115	Dark Gray
249092	Sun Yellow
249061	Semi-Gloss Black
249862	Marigold
249122	Black
249103	Khaki
249125	Almond
249847	Chestnut
249099	Navajo White
249102	Kona Brown
249110	Ivory
249111	Hunter Green
249860	Semi-Gloss Ivory Bisque
249853	Semi-Gloss Hunter Green
249060	Semi-Gloss White
249100	Meadow Green
249090	White
249104	Key Lime
267116	Seaside
283189	Coral
283190	Ocean Mist

PRODUCTS (cont.)

Satin Finish Unless Otherwise Noted

AEROSOL	DESCRIPTION
249845	Clear
249085	Aqua
249087	Matte Clear
249062	Wildflower Blue
249063	Sweet Pea
249854	Midnight Blue
249082	Colonial Red
249066	Slate Blue
249083	Claret Wine
249079	French Lilac
249068	Paprika
249069	Oregano
249084	Cinnamon
249128	Aluminum
249065	Strawflower
249855	Stone Gray
249064	Summer Squash
249857	London Gray
249080	Fossil
249078	Granite
249070	Nutmeg
249844	Canyon Black
249081	Espresso
249127	Flat Black
249077	Green Apple
249073	Ivory Silk
249072	Leafy Green
249076	Heirloom White
249071	Moss Green
249126	Flat White
249074	Hunt Club Green
249843	Blossom White
267118	Warm Caramel
277994	Poppy Red
277991	Oasis Blue
283188	Magenta

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.



TECHNICAL DATA

PAINTER'S TOUCH® ULTRA COVER 2X ENAMEL SPRAYS

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to thoroughly dry. All surfaces must be dry at time of application. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces to create a surface profile.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRIMING

Use of a Painter's Touch® primer provides excellent adhesion and hiding and is especially recommended for bare wood and metal. The following primers are recommended:

249086	Red Primer
249088	Gray Primer
249846	Black Primer
249058	White Primer

PRODUCT APPLICATION (cont.)

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle **DO NOT STRIKE CAN**. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 20 minutes, to handle in 1 hour, and is fully dry in 24 hours. Apply a second coat or Clear coat within 1 hour or after 48 hours. Apply the clear coat in 2-3 light coats a few minutes apart.

CLEAN-UP

Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.



TECHNICAL DATA

PAINTER'S TOUCH® ULTRA COVER 2X ENAMEL SPRAYS

PHYSICAL PROPERTIES

		ULTRA COVER 2X ENAMEL SPRAYS
Resin Type		Acrylic Modified Alkyd
Pigment Type		Varies with Color
Solvents		Acetone, Toluene, Xylene
MIR		Gloss & Non-Flats - 1.4 Max Flats - 1.20 Max Clear - 1.50 Max
Fill Weight		12 ounces
Recommended Dry Film Thickness (DFT) per Coat		1.0-2.0 mils (25-50 μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		7-8 sq.ft./can (0.63-0.72 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	20 minutes
	Handle	1 hour
	Recoat	Within 1 hour or after 48 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.